

Order No./계약번호 : 01S5526434

PO No./주문번호 : ACR2203BJ-CC11X
(POSCO-CTPC)Supplier
/주문자 : POSCO INTERNATIONAL CORPORATIONCommodity : COLD ROLLED COIL
/품명Customer
/고객사 : POSCO-CTPCSpec & Type : EN-DC03
/규격

Size/치수	Product No. /제품번호	Quantity /수량	Weight /중량 (kg)	Heat No. /제강번호	Position	Tensile Test /인장시험			Plastic Anisotropy Test r90	Roughness Ra (μ m)	Division	Chemical Composition/화학적성분				
						YP (N/mm ²)	TS (%)	EL (%)				C (%)	Si (%)	Mn (%)	P (%)	S (%)
1.2x1179xC	CSE5868A	1	9,490	SP23158	B	161	296	46	2.30	0.95	L	0.0019	0.001	0.092	0.0098	0.0051
1.2x1179xC	CSE5868B	1	9,480	SP23158	B	161	296	46	2.30	0.95	L	0.0019	0.001	0.092	0.0098	0.0051
1.2x1179xC	CSE5868C	1	9,580	SP23158	B	161	296	46	2.30	0.95	L	0.0019	0.001	0.092	0.0098	0.0051
*** Sub Total (010) ***		3	28,550 (kg)	< Not Welded >												
*** Grade Total ***		3	28,550 (kg)													

* Position - T : Top, M : Middle, B : Bottom
* Tensile Test. Direction : Transversal, Gauge Length : 80 mm(Rectangular),
YP Method : Low Point
* Division - L : Ladle Analysis

We hereby certify that the material herein has been made in accordance with the order and is fully in compliance.

Legal sanction can be imposed on forging. Improper use of product can cause safety issues.

Surveyor To :

Park, Junyoung



Order No./계약번호 : 01S5526434

PO No./주문번호 : ACR2203BJ-CC11X
(POSCO-CTPC)Supplier
/주문자 : POSCO INTERNATIONAL CORPORATIONCommodity : COLD ROLLED COIL
/품명Customer
/고객사 : POSCO-CTPCSpec & Type : EN-DC03
/규격

Size/치수	Product No. /제품번호	Quantity /수량	Weight /중량 (kg)	Heat No. /제강번호	Position	Tensile Test /인장시험			Plastic Anisotropy Test r90	Roughness Ra (μ m)	Division	Chemical Composition/화합성분				
						YP (N/mm ²)	TS (%)	EL (%)				C (%)	Si (%)	Mn (%)	P (%)	S (%)
1.2x1179xC	CSED078A	1	9,450	SQ80877	B	179	296	44	2.20	1.06	L	0.0020	0.002	0.097	0.0097	0.0038
1.2x1179xC	CSED078B	1	9,440	SQ80877	B	179	296	44	2.20	1.06	L	0.0020	0.002	0.097	0.0097	0.0038
1.2x1179xC	CSED078C	1	9,660	SQ80877	B	179	296	44	2.20	1.06	L	0.0020	0.002	0.097	0.0097	0.0038
*** Sub Total (010) ***		3	28,550 (kg)			< Not Welded >										
*** Grade Total ***		3	28,550 (kg)													
*** Grand Total ***		6	57,100 (kg)													
=== Last Item ===																

* Position - T : Top, M : Middle, B : Bottom
* Tensile Test. Direction : Transversal, Gauge Length : 80 mm(Rectangular),
YP Method : Low Point
* Division - L : Ladle Analysis

We hereby certify that the material herein has been made in accordance with the order and is fully in compliance.

Legal sanction can be imposed on forging. Improper use of product can cause safety issues.

Surveyor To :

Park, Junyoung

